

First Principles Study on the Electronic Properties of $\text{Ca}_{10}(\text{Pt}_3\text{As}_8)(\text{Fe}_2\text{As}_2)_5$

Elizabeth Hilliard

Advisors: Dr. M. Jarrell and Dr. J. Moreno

Graduate Student Advisor: Chinedu Ekuma

Louisiana State University, Center for Computation and Technology,
Research Experience for Undergraduates



Center for
Computation & Technology



LA-SIGMA
Louisiana Alliance for Simulation-Guided Materials Applications



Rensselaer

Outline

- Motivations: Why $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$?
- Methods: Density Functional Theory (DFT)
- Results: Ground state of $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$
- Conclusions and Future Work


Motivations: Why $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$?

Superconductors


- Conduct with zero electrical resistance
- Expel magnetic fields
- Powerful electromagnets - important for technology
- Higher critical temperature of some materials still not understood

Motivations: Why $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$?

- New class: Iron-based High- T_c Superconductors
- Superconductivity could have to do with magnetic configuration
- Some research has been done, but ground state previously unknown



Methods: Density Functional Theory (DFT)




- DFT is a first-principle ab-initio method utilized in obtaining the properties of materials
- WIEN2k is an all-electron code with proven high accuracy.
- For these calculations, we ran WIEN2k on the LONI supercomputer QueenBee

Results: $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$ Ground State Energy Calculation


- Calculations were run for each of three magnetic configurations: nonmagnetic, ferromagnetic, and antiferromagnetic
- Lowest energy configuration: Antiferromagnetic
- Difference between antiferromagnetic energy and next level up, ferromagnetic, is 0.677 eV/Fe

Results: $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$ Density of States (DOS)

Comparison of the DOS for the nonmagnetic (NM), ferromagnetic (FM), and antiferromagnetic (AFM) configurations.



Results: $Ca_{10}(Pt_3As_8)(Fe_2As_2)_5$ Electronic Band Structure



The calculated electronic band structure in the antiferromagnetic configuration.

Conclusions and Future Work

- Antiferromagnetic ground state, followed by the ferromagnetic phase
- Importance: Doped cases can now be researched more effectively
- Fe-based superconductors could help us understand how superconductors come about

Acknowledgements

- Thanks to Dr. Juana Moreno, Dr. Mark Jarrell, and Chinedu Ekuma for advising me this summer
- This work is supported by the National Science Foundation (NSF) Award No. LA-SiGMA EPS-1003897 with additional support from the Center for Computation and Technology at Louisiana State University
- This material is based upon work supported by the Louisiana Optical Network Institute (LONI).

Questions?

References

- P. Blaha, K. Schwarz, G. K. H. Madsen, D. Kvasnicka and J. Luitz, WIEN2k, An Augmented Plane Wave + Local Orbitals Program for Calculating Crystal Properties (Karlheinz Schwarz, Techn. Universitat Wien, Austria), 2001. ISBN 3-9501031-1-2
- N. Ni, J. M. Allred, B. C. Chan, and R. J. Cava, PNAS. 108, E1019 (2011).
- M. Neupane, C. Liu, et al arXiv 1110.4687v1, (2011)